

AMERCOAT® 68 HS

DESCRIPTION

Three-component, zinc rich epoxy

PRINCIPAL CHARACTERISTICS

- >80% zinc in dry film
- Provides outstanding corrosion resistance
- Fast dry times for rapid topcoating
- AMERCOAT 861 accelerator can be used for low temperature curing
- Qualified primer for steel potable water tanks per ANSI/NSF 61 (U.S. production only)

COLOR AND GLOSS LEVEL

- Reddish gray
- Flat

Note: Green color will be made-to-order, Gray color available in Asia

BASIC DATA AT 68°F (20°C)

Data for mixed product	
Number of components	Three
Mass density	3.2 kg/l (26.7 lb/US gal)
Volume solids	70 ± 2%
VOC (Supplied)	max. 2.4 lb/US gal (approx. 288 g/l)
Temperature resistance (Continuous)	To 400°F (204°C)
Recommended dry film thickness	2.0 - 5.0 mils (50 - 125 µm) depending on system
Theoretical spreading rate	561 ft ² /US gal for 2.0 mils (14.0 m ² /l for 50 µm)
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry Powder: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time
- Color will drift at elevated temperatures
- Continuous temperature resistance should be less than 5% of the time, and maximum 24 hours

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Coating performance is proportional to the degree of surface preparation. All previous coats must dry and free of contaminants



AMERCOAT® 68 HS

Steel

- Abrasive blast with an angular abrasive to an SSPC SP-6 or higher. Achieve a surface profile of 1.0 – 3.0 mils (25 – 75 µm)
- Higher surface profiles up to 5 mils are acceptable, but the product must be applied to achieve a minimum film thickness of 2.5 mils above the peaks of the profile.
- Apply this product as soon as possible to prevent blasted surface from rusting.
- Keep moisture, oil, grease and other organic matter off surface before coating
- For touch up and repair, power tool cleaning in accordance with SSPC SP-3 is acceptable for small areas and SSPC SP-11 should be specified for large repair areas where blasting is not allowed.

Substrate temperature and application conditions

- Surface temperature during application should be between 40°F (4°C) and 120°F (49°C)
- With accelerator: Surface temperature during application should be between 32°F (0°C) and 100°F (38°C)
- Surface temperature during application should be at least 5°F (3°C) above dew point
- Relative humidity during application and curing should not exceed 85%

Notes:

- Extreme caution should be taken to ensure there is no ice on the surface in cold weather
- Product can be applied without accelerator at surface and air temperatures down to 40°F. Material temperature must be maintained at 50°F to 90°F at the time of application. Due to the long curing time at this temperatures when accelerator is not used, it is recommended that temperatures above 50°F are expected within 12 hours of application. Coated surfaces should be protected from moisture until dry through time is reached.
- If abrasive blast preparation is not possible, use SSPC-SP11, power tool cleaning to bare metal (ISO-St3)

SYSTEM SPECIFICATION

- Primers: Direct to metal, can be used to touch up inorganic zincs such as DIMETCOTE 9-SERIES
- Topcoats: AMERSHIELD, PSX 700, AMERCOAT 450 H, AMERLOCK 2/400, AMERCOAT 385, AMERCOAT 370, AMERCOAT Epoxies, PITTPROTECT Epoxies, DURATHANE DTM, PITTHANE ULTRA

SECONDARY SURFACE PREPARATION

- During storage and construction, contamination of the prefabrication primer should be limited

Mix as packaged

- Pre-mix base component with a pneumatic air mixer at moderate speeds to homogenize the container. Add hardener to base and agitate with a power mixer for 1-2 minutes until completely dispersed. Add powder component slowly under agitation until fully mixed. Strain the mixture from one container to another through a 30 mesh filter/strainer to remove any undispersed lumps
- Agitate continuously during application

Pot life

16 hours at 70°F (21°C)

Note: See ADDITIONAL DATA – Pot life



AMERCOAT® 68 HS

Application

- Area should be sheltered from airborne particulates and pollutants
- Ensure good ventilation during application and curing
- Provide shelter to prevent wind from affecting spray patterns

Material temperature

Material temperature during application should be between 50°F (10°C) and 90°F (32°C)

Air spray

- A moisture and oil trap in the main line is essential. Product is sensitive to moisture contamination
- Separate air and fluid pressure regulators and a moisture and oil trap in the main air supply line are recommended.
- Use standard conventional equipment

Recommended thinner

THINNER 21-06 (AMERCOAT 65) (xylene), THINNER 21-25 (AMERCOAT 101) (recommended for > 90°F (32°C), THINNER 91-82 (AMERCOAT T-10)

Volume of thinner

0 - 10%

Nozzle orifice

Approx. 0.070 in (1.8 mm)

Airless spray

- 45:1 pump or larger

Recommended thinner

THINNER 21-06 (AMERCOAT 65) (xylene), THINNER 21-25 (AMERCOAT 101) (recommended for > 90°F (32°C), THINNER 91-82 (AMERCOAT T-10)

Volume of thinner

0 - 7%

Nozzle orifice

0.017 – 0.019 in (approx. 0.43 – 0.48 mm)

AMERCOAT® 68 HS

Brush/roller

- Use a high-quality natural-bristle brush. Brush application is only recommended for small touch-up and/or repair areas. Roller application is not recommended
- Ensure the brush/roller is well-loaded to avoid air entrainment. Level air bubbles with a brush. Multiple coats may be necessary to achieve adequate film build

Recommended thinner

THINNER 21-06 (AMERCOAT 65) (xylene), THINNER 21-25 (AMERCOAT 101) (recommended for > 90°F (32°C)), THINNER 91-82 (AMERCOAT T-10)

Volume of thinner

0 – 6%

Cleaning solvent

Amercoat 12 Cleaner (Thinner 90-58) or Amercoat 65 Thinner (Thinner 21-06)

Note: All application equipment must be cleaned immediately after use

ADDITIONAL DATA

Overcoating interval for DFT up to 3.0 mils (75 µm)					
Overcoating with...	Interval	32°F (0°C)	50°F (10°C)	70°F (21°C)	90°F (32°C)
various two-pack epoxy and polyurethane coatings	Minimum	N/A	6 hours	2 hours	1 hour
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited

Notes:

- Surface must be power washed as needed to remove all surface contaminants including zinc salts. Surface must be clean and dry
- Product does not require sanding / abrading to overcoat. However, the surface must be dry and free of contaminants such as ambient contamination or zinc salts. Power washing may be used to remove zinc salts and other contaminants.

Overcoating interval with AMERCOAT 861 accelerator for DFT up to 3.0 mils (75 µm)					
Overcoating with...	Interval	32°F (0°C)	50°F (10°C)	70°F (21°C)	90°F (32°C)
itself	Minimum	16 hours	3 hours	1 hour	30 minutes
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited
PSX 700	Minimum	16 hours	4 hours	1.5 hours	45 minutes
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited

Notes:

- Surface must be power washed as needed to remove all surface contaminants including zinc salts. Surface must be clean and dry
- With force cure capabilities (oven temperatures of 140°F (60°C) to 180°F (82°C)), product can be overcoated after 5-15 minutes. Allow 5-10 minutes flash off prior to heating past 120°F (49°C). Addition of AMERCOAT 861 accelerator is recommended for this procedure.
- Product does not require sanding / abrading to overcoat. However, the surface must be dry and free of contaminants such as ambient contamination or zinc salts. Power washing may be used to remove zinc salts and other contaminants.



AMERCOAT® 68 HS

Curing time for DFT up to 3.0 mils (75 µm)		
Substrate temperature	Dry to touch	Dry to handle
40°F (4°C)	6 hours	36 hours
50°F (10°C)	90 minutes	18 hours
70°F (21°C)	30 minutes	4 hours
90°F (32°C)	15 minutes	2.5 hours

curing time for DFT up to 3.0 mils with Amercoat 861 Accelerator		
Substrate temperature	Dry to touch	Dry to handle
32°F (0°C)	6 hours	48 hours
50°F (10°C)	1 hour	8 hours
70°F (21°C)	20 minutes	3 hours
90°F (32°C)	10 minutes	1.5 hours

Pot life (at application viscosity)	
Mixed product temperature	Pot life
50°F (10°C)	24 hours
70°F (21°C)	16 hours
90°F (32°C)	8 hours

Pot life (at application viscosity) with AMERCOAT 861 accelerator	
Mixed product temperature	Pot life
50°F (10°C)	16 hours
70°F (21°C)	9 hours
90°F (32°C)	5 hours

NSF application criteria for potable water



AMERCOAT® 68 HS

Application criteria for DFT up to 4.0 mils (100 µm)	
Application criteria	Value
Number of coats	1
Maximum dry film thickness	4.0 mils (100 µm)
Minimum Recoat Time	16 hours
Minimum Cure to Service	Please refer to the NSF listing for the epoxy lining
Thinner	PPG 21-06 / Amercoat 65
Maximum thinner use	6%
Minimum tank size	50,000 gallons
Approved NSF Epoxy Linings	Amerlock 2, Amerlock 2 VOC, Novaguard 810, Amercoat 133

Notes:

- Please reference the up-to-date listing at <http://info.nsf.org/Certified/PwsComponents/Listings.asp?Company=02460&Standard=061>
- U.S. production only

Product Qualifications

- RCSC Class B slip coefficient for high strength bolted connections
- SSPC Paint 20, Type II, Level 2
- Zinc dust meets ASTM D520 Type 3 standards
- Qualified for ANSI/NSF Standard 61 (potable water). For NSF application instructions, please visit the following website: <http://www.nsf.org/certified-products-systems/>

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.



AMERCOAT® 68 HS

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgmc.com. The English text of this sheet shall prevail over any translation thereof.

Packaging: Available in 1-gallon and 4-gallon kits

Product code	Description
AT68HS-A	Reddish Gray Base
AT68HS-5	Green Base
AT68HS-B	Hardener
AT68HS-P	Zinc Powder

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

